

QUALITY REMARK: AEPD

QUALITY REQUIREMENT NUMBER 110

MATERIAL SAMPLES REPRESENTATIVE OF EACH COMPONENT FORGING IN THE FINAL HEAT TREATED CONDITION SHALL BE PERMANENTLY RETAINED BY THE SUPPLIER. OF MATERIAL SAMPLES MAY BE EITHER TEST RING SECTIONS, MOUNTS FROM TEST RINGS, OR SMALL SPECIMENS TAKEN FROM THE PART THAT ARE A MINIMUM OF .50 INCH IN EACH DIRECTION. SAMPLES MUST BE TRACEABLE TO SERIAL NUMBER AND PART NUMBER. MOUNTS FROM TEST RINGS ARE PREFERRED. RETRIEVAL OF THE SAMPLE FROM STORAGE AT THE PURCHASER'S REQUEST SHALL BE WITHIN FIVE (5) WORKING DAYS.