

QUALITY REMARK: AEPD

QUALITY REQUIREMENT NUMBER 698

SPECIFICATION C50TF20A A-286 ALLOY TEST BARS SHALL CONFORM TO THE FOLLOWING: SOLUTION HEAT TREAT AT 1650 DEG. F, 2 HOURS MIN. AND AIR COOL. AGE HARDEN AT 1325 DEG. F, 16-19 HOURS AND AIR COOL.